

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C30B 9/00, 29/40, 11/00	A1	(11) International Publication Number: WO 98/55671 (43) International Publication Date: 10 December 1998 (10.12.98)
(21) International Application Number: PCT/PL98/00023 (22) International Filing Date: 3 June 1998 (03.06.98) (30) Priority Data: P.320392 5 June 1997 (05.06.97) PL (71) Applicant (for all designated States except US): CENTRUM BADAN WYSOKOCIŚNIENIOWYCH POLSKIEJ AKADEMII NAUK [PL/PL]; ul. Sokołowska 29/37, PL-01-142 Warszawa (PL). (71)(72) Applicants and Inventors: ŁUCNLIK, Bolesław [PL/PL]; ul. Gwiazdzista 27 m 93, PL-01-651 Warszawa (PL). SUSKI, Tadeusz [PL/PL]; ul. Lachmana 2 m 70, PL-02-786 Warszawa (PL). WRÓBLEWSKI, Mirosław [PL/PL]; ul. Nowolipie 26 m 85, PL-01-011 Warszawa (PL). (72) Inventors; and (75) Inventors/Applicants (for US only): POROWSKI, Sylwester [PL/PL]; ul. Wieniawskiego 5/7, PL-01-572 Warszawa (PL). BOCKOWSKI, Michał [PL/PL]; ul. Klaudyń, 32 m 311, PL-01-168 Warszawa (PL). GRZEGORY, Izabella [PL/PL]; ul. Nałkowskiej, 9 m 10, PL-01-886 Warszawa (PL). KRUKOWSKI, Stanisław [PL/PL]; ul. Zaranie		(81) Designated States: JP, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: THE METHOD OF FABRICATION OF HIGHLY RESISTIVE GaN BULK CRYSTALS (57) Abstract This method according to the invention allows the fabrication of bulk GaN crystals of high specific resistivity. This is achieved by the crystallization of GaN from the solution of atomic nitrogen in molten mixture of metals, containing gallium and Periodic Table group II metals: magnesium, calcium, zinc, beryllium, cadmium, under high pressure of nitrogen, in the temperature gradient. These crystals can be used to fabrication of excellent single crystalline GaN substrates for deposition of the homoepitaxial layers and structures for the optoelectronic applications.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Faso	GR	Greece		Republic of Macedonia	TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

The method of fabrication of highly resistive GaN bulk crystals

Field of the Invention

This Invention relates to the method of fabrication of highly resistive GaN bulk crystals for manufacturing of optoelectronic devices.

Background of the Invention

According to the present state of the art of growth of single crystals there are not known methods of manufacturing of highly resistive GaN bulk crystals.

Object and Summary of the Invention

According to the Invention, GaN crystallization is effected in the solution of atomic nitrogen in molten mixture of the metals containing gallium in the concentration not lower than 90 at % and at least one of Periodic Table group II metals: Mg, Ca, Be, Zn, Cd. in the concentration: 0.01 - 10 at % in order to reduce the concentration of free electron carriers in the crystal by change of microscopic growth mechanism leading to the improvement of the stoichiometry and compensation on nonintentionally introduced donor impurities. The process is conducted under nitrogen pressure 0.5 - 2.0 GPa and in the temperature 1300 - 1700 °C in order to assure the stability of GaN and high concentration of nitrogen in liquid solution.

Crystallization is conducted with the temperature gradient not smaller than $10^{\circ}\text{C}/\text{cm}$, which assures low supersaturation in the growth zone, necessary to obtain GaN crystal growth velocity lower than 0.2 mm/h , necessary for stable growth of large size crystals.

In the results of the growth process hexagonal GaN plate-like crystals are obtained, having the specific resistivity $10^4 - 10^8 \Omega\text{cm}$, characterized by high structural quality and the lattice parameters close to the perfect crystal. These so obtained crystals, are not available at present, and can be used as perfect substrates for unstrained homoepitaxial GaN layers.

The subject of the Invention is demonstrated on the examples of applications.

Example 1

The molten mixture of semiconductor purity metals consisting of 99.5 at. % of gallium and 0.5 at. % of magnesium is poured into the vertically configured graphite crucible under the shield of inert gas. The crucible is located into the three-zone graphite furnace which is then positioned inside the high pressure vessel, which in the first stage is evacuated to the vacuum level of 10^{-5} Torr. The system is annealed in the vacuum in the temperature 800°C during 12 hours. After the annealing, the vessel is filled with nitrogen of 6N purity achieving the initial pressure of 10-15 MPa. Then the gas is compressed to the pressure of 1.5 GPa and after the compression, the crucible is heated to the temperature of 1550°C in such a way that the temperature along the crucible axis is kept constant. Then the temperature of the lower end of the crucible is lowered by 30°C obtaining the temperature gradient along the axis of the crucible. These conditions of the process are preserved during the period of 120 hours. After

120 of crystallization, the system is cooled down with the rate of 5°C/min to the room temperature and after that the nitrogen pressure is lowered to the atmospheric pressure. After the extraction of the crucible from the high pressure vessel, the crucible is warmed up to the temperature 50°C and the molten metal is poured out from the crucible. At the bottom of the crucible there are GaN crystals in the form of hexagonal platelets of the size of 6 - 8 mm. The GaN crystals are extracted from the crucible and etched in aqua regia in order to remove the remaining part of the metal.

GaN crystals, obtained in this process characterize by the specific resistivity equal to $10^6 \Omega\text{cm}$ and high structural quality. The halfwidth of (0004) reflection of x-ray αCuK line is 20 - 30 arc sec, and the a and c lattice parameters are very uniform and are equal to: 3.1877 Å and 5.1848 Å, respectively.

We claim:

1. The method of fabrication of highly resistive GaN bulk crystals, characterized by crystallization from the solution of atomic nitrogen in the molten mixture of metals, containing gallium in the concentration not lower than 90 at % and the Periodic Table group II metals magnesium, calcium, zinc, beryllium, cadmium in the concentration of 0.01 - 10 at% under the nitrogen pressure 0.5 - 2.00 GPa.
2. The method of fabrication of highly resistive GaN bulk crystals according to Claim 1 characterized by the crystallization temperature 1300 - 1700°C.
3. The method of fabrication of highly resistive GaN bulk crystals, according to Claim 1 characterized by the temperature gradient not higher than 10°C/cm.

INTERNATIONAL SEARCH REPORT

Internat	Application No
PCT/P	/00023

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C30B9/00 C30B29/40 C30B11/00

According to International Patent Classification(IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C30B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P, X	PATENT ABSTRACTS OF JAPAN vol. 98, no. 5 & JP 10 007496 A (HITACHI CABLE LTD) see abstract ---	1-3
X	WO 95 04845 A (CENTRUM BADAN WYSOKOCISNIENIOWYCH) 16 February 1995 see page 11, line 3 - line 22; example 1 ---	1-3
X	FR 2 313 976 A (LABORATOIRES D'ELECTRONIQUE ET DE PHYSIQUE APPLIQUEE LEP) 7 January 1977 see page 2, line 8 - line 9; claim 1 --- -/--	1-3

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

6 October 1998

Date of mailing of the international search report

16/10/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Cook, S

INTERNATIONAL SEARCH REPORT

Internat^l Application No
PCT/PL 8/00023

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	POROWSKI ET AL: "Thermodynamical properties of III-V nitrides and crystal growth of GaN at high N ₂ pressure" JOURNAL OF CRYSTAL GROWTH., vol. 178, 2 June 1997, pages 174-188, XP004084984 AMSTERDAM NL see page 181 ---	1-3
A	KARPINSKI ET AL: "Equilibrium pressure of N ₂ over GaN and high pressure solution growth of GaN" JOURNAL OF CRYSTAL GROWTH., vol. 66, 1984, pages 1-10, XP002079608 AMSTERDAM NL see the whole document ---	1-3
A	WO 97 13891 A (CENTRUM BADAN WYSOKOCISNIENIOWYCH) 17 April 1997 see example 1 ---	1-3
A	YAMANE ET AL: "Preparation of GaN single crystals using a Na flux" CHEMISTRY OF MATERIALS, vol. 9, February 1997, pages 413-416, XP000686510 WASHINGTON US -----	

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/PL/00023

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9504845 A	16-02-1995	PL 300019 A	20-02-1995
		AU 6584894 A	28-02-1995
		CA 2168871 A	16-02-1995
		EP 0713542 A	29-05-1996
		JP 9512385 T	09-12-1997
		US 5637531 A	10-06-1997
FR 2313976 A	07-01-1977	DE 2624958 A	23-12-1976
		GB 1551403 A	30-08-1979
		JP 51151299 A	25-12-1976
WO 9713891 A	17-04-1997	AU 7346396 A	30-04-1997